


Detail Gradation Statistical Summary Report

Plant 01 Atlanta Sand-Burke Pit
Product 2 B-Burke Concrete Sand
Specification 2 B Burke Concrete Sand
Period 02/01/2025 - 02/28/2025

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
3/8" (9.5mm)	19	100	100	100	0	0.0		100-100	100.0
#4 (4.75mm)	19	100	99	100	1	0.2		95-100	100.0
#8 (2.36mm)	19	99	98	99	1	0.5			
#16 (1.18mm)	19	90	85	92	7	1.9		45-95	99.6
#30 (.6mm)	19	59	52	65	13	3.7			
#50 (.3mm)	19	19	14	25	11	3.0		8-30	100.0
#100 (.15mm)	19	1	0	2	2	0.6		0-10	100.0
Pan	20	0.0	0.0	0.0	0.0	0.00			
FM	19	2.327	2.170	2.496	0.326	0.0846			
SE	4	92.750	85.000	98.000	13.000	5.5000			
Wash Loss (#200/75um)	3	1.788	1.716	1.853	0.137	0.0688			



Comments

Query

Query Selections
Date Created 03/03/2025
Date Range 02/01/2025 - 02/28/2025
Plant Burke Pit
Sample Type Shipping
Sample Method Load-Out Face