




Detail Gradation Statistical Summary Report

Plant 03-Fort Gordon Plant
Product 2A-Fort Gordon Concrete Sand
Specification Fort Gordon Concrete Sand
Period 02/01/2025 - 02/28/2025

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
3/8" (9.5mm)	20	100.0	100.0	100.0	0.0	0.00		100-100	100.0
#4 (4.75mm)	20	99.7	99.4	100.0	0.6	0.17		95-100	100.0
#8 (2.36mm)	20	97.9	97.4	98.2	0.8	0.28			
#16 (1.18mm)	20	88.3	87.5	89.6	2.1	0.59		45-95	100.0
#30 (0.6mm)	20	50.5	47.2	56.9	9.7	2.33			
#50 (0.3mm)	20	13.9	11.7	19.8	8.1	2.18		5-30	100.0
#100 (0.15mm)	20	0.7	0.3	1.4	1.1	0.24		0-10	100.0
Pan	20	0.00	0.00	0.00	0.00	0.000			
FM	20	2.489	2.361	2.549	0.188	0.0507			
SE	4	84.000	80.000	86.000	6.000	2.8284			
Wash Loss (#200/75um)	4	0.429	0.345	0.505	0.160	0.0686			



Comments

Query Query Selections
 Date Created 02/28/2025
 Date Range 02/01/2025 - 02/28/2025
 Plant Fort Gordon Plant
 Sample Type Shipping
 Sample Method Load-Out Face