




Detail Gradation Statistical Summary Report

Plant 03-Fort Gordon Plant
Product 2A-Fort Gordon Concrete Sand
Specification Fort Gordon Concrete Sand
Period 04/01/2025 - 04/30/2025

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
3/8" (9.5mm)	21	100.0	100.0	100.0	0.0	0.00		100-100	100.0
#4 (4.75mm)	21	99.6	99.3	99.9	0.6	0.18		95-100	100.0
#8 (2.36mm)	21	96.9	95.7	98.1	2.4	0.59			
#16 (1.18mm)	21	82.9	78.1	89.5	11.4	3.03		45-95	100.0
#30 (0.6mm)	21	40.2	32.9	53.4	20.5	5.55			
#50 (0.3mm)	21	10.6	7.7	15.4	7.7	2.05		5-30	99.7
#100 (0.15mm)	21	0.7	0.4	1.1	0.7	0.19		0-10	100.0
Pan	21	0.00	0.00	0.00	0.00	0.000			
FM	21	2.691	2.453	2.840	0.387	0.1046			
SE	4	84.500	84.000	85.000	1.000	0.5774			
Wash Loss (#200/75um)	4	0.488	0.316	0.729	0.413	0.1736			



Comments

Query Query Selections
 Date Created 05/02/2025
 Date Range 04/01/2025 - 04/30/2025
 Plant Fort Gordon Plant
 Sample Type Shipping
 Sample Method Load-Out Face