


## Detail Gradation Statistical Summary Report

**Plant** 01 Atlanta Sand-Burke Pit  
**Product** 2 B-Burke Concrete Sand  
**Specification** 2 B Burke Concrete Sand  
**Period** 04/01/2026 - 04/30/2026

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
3/8" (9.5mm)	22	100	100	100	0	0.0		100-100	100.0
#4 (4.75mm)	22	100	100	100	0	0.0		95-100	100.0
#8 (2.36mm)	22	98	97	99	2	0.6			
#16 (1.18mm)	22	87	78	91	13	3.1		45-95	99.5
#30 (.6mm)	22	54	48	62	14	4.3			
#50 (.3mm)	22	17	12	24	12	2.9		8-30	99.9
#100 (.15mm)	22	2	1	4	3	0.9		0-10	100.0
Pan	22	0.0	0.0	0.0	0.0	0.00			
FM	22	2.421	2.201	2.542	0.341	0.0959			
SE	4	90.750	88.000	93.000	5.000	2.0616			
Wash Loss (#200/75um)	1	0.991	0.991	0.991	0.000				



**Comments**

**Query**

Query Selections  
Date Created 05/01/2026  
Date Range 04/01/2026 - 04/30/2026  
Plant Burke Pit  
Sample Type Shipping  
Sample Method Load-Out Face