


## Detail Gradation Statistical Summary Report

**Plant** 01 Atlanta Sand-Burke Pit  
**Product** 2 B-Burke Concrete Sand  
**Specification** 2 B Burke Concrete Sand  
**Period** 05/01/2026 - 05/31/2026

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
3/8" (9.5mm)	20	100	100	100	0	0.0		100-100	100.0
#4 (4.75mm)	20	100	100	100	0	0.0		95-100	100.0
#8 (2.36mm)	20	98	97	100	3	0.8			
#16 (1.18mm)	20	88	83	93	10	2.9		45-95	99.2
#30 (.6mm)	20	57	39	73	34	8.0			
#50 (.3mm)	20	18	10	24	14	4.2		8-30	98.9
#100 (.15mm)	20	2	1	3	2	0.7		0-10	100.0
Pan	20	0.0	0.0	0.0	0.0	0.00			
FM	19	2.376	2.104	2.635	0.531	0.1425			
SE	4	86.750	85.000	88.000	3.000	1.2583			
Wash Loss (#200/75um)	5	1.020	0.771	1.445	0.674	0.2747			



**Comments**

**Query**

Query Selections  
Date Created 06/01/2026  
Date Range 05/01/2026 - 05/31/2026  
Plant Burke Pit  
Sample Type Shipping  
Sample Method Load-Out Face