


Detail Gradation Statistical Summary Report

Plant 01 Atlanta Sand-Burke Pit
Product 2 B-Burke Concrete Sand
Specification 2 B Burke Concrete Sand
Period 08/01/2026 - 08/31/2026

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
3/8" (9.5mm)	21	100	100	100	0	0.0		100-100	100.0
#4 (4.75mm)	21	100	100	100	0	0.0		95-100	100.0
#8 (2.36mm)	21	98	97	99	2	0.6			
#16 (1.18mm)	21	86	81	90	9	2.4		45-95	100.0
#30 (.6mm)	21	54	45	63	18	4.9			
#50 (.3mm)	21	16	10	21	11	2.9		8-30	99.7
#100 (.15mm)	21	2	1	3	2	0.7		0-10	100.0
Pan	21	0.0	0.0	0.0	0.0	0.00			
FM	21	2.441	2.236	2.654	0.418	0.1057			
SE	4	91.500	88.000	95.000	7.000	4.0415			
Wash Loss (#200/75um)	4	1.227	0.962	1.497	0.535	0.2207			



Comments**Query**

Query Selections

Date Created 09/01/2026

Date Range 08/01/2026 - 08/31/2026

Plant Burke Pit

Sample Type Shipping

Sample Method Load-Out Face