


Detail Gradation Statistical Summary Report

Plant 01 Atlanta Sand-Burke Pit
Product 2 B-Burke Concrete Sand
Specification 2 B Burke Concrete Sand
Period 09/01/2026 - 09/30/2026

Sieve/Test	Tests	Average	Min	Max	Range	St Dev	Target	Specification	PWS
3/8" (9.5mm)	21	100	100	100	0	0.0		100-100	100.0
#4 (4.75mm)	21	100	100	100	0	0.0		95-100	100.0
#8 (2.36mm)	21	98	97	99	2	0.7			
#16 (1.18mm)	21	85	78	90	12	3.2		45-95	99.9
#30 (.6mm)	21	50	41	66	25	6.2			
#50 (.3mm)	21	14	10	21	11	3.3		8-30	96.5
#100 (.15mm)	21	1	1	2	1	0.4		0-10	100.0
Pan	21	0.0	0.0	0.0	0.0	0.00			
FM	21	2.517	2.231	2.740	0.509	0.1290			
SE	5	89.000	85.000	91.000	6.000	2.5495			
Wash Loss (#200/75um)	4	1.466	1.030	1.723	0.693	0.3183			



Comments**Query**

Query Selections

Date Created 10/01/2026

Date Range 09/01/2026 - 09/30/2026

Plant Burke Pit

Sample Type Shipping

Sample Method Load-Out Face